



label 料号: label Part NO.: Q40G0002-059-01A	
客户 Customer	TPV
型号 Model	WL-211
销向 Sales Area	
安规审核Safety parts: Yes <input checked="" type="checkbox"/> No <input type="checkbox"/>	
内销中文字体要求高度1.8mm以上 Yes <input checked="" type="checkbox"/> No <input type="checkbox"/>	
针对带有UL logo的标签,其厂家须在最小包装上标示出: Recognized Component Mark  公司名称, 型号及 UL file no.	
条码印刷: barcode print: 1. 所有条码透明等级: C级及以上, 客户有特殊要求除外:	
<b>REVISION</b>	
<b>VERSION A</b> 版本变更说明: Version Changed Description:	
<b>备注Remark:</b>  JUN-11-15 WR.ZHENG	
捷联电子(福建)有限公司 TPV Electronics (Fujian) Co., Ltd. 地址(Add): 中国福建省福清市元洪路上部 Shanghong, Yuanhong Road, Fuqing City, Fujian Province, China 电话(Tel): +86-591-85285555 85285559 传真(Fax): +86-591-85285447 邮编(Postcode): 350301	



**NOTE:**

1. 印刷如上图

Printing as the drawing

2. 尺寸如图 (公差+/-0.2mm)

Size: See the drawing (tolerance +/-0.2mm)

3. 材质: 80g铜版纸带背胶

Material: Material: 80g ART PAPER with glue on the backside

4. 底色: 白色; 字体颜色: 黑色

5. 贴附位置: 贴于铁壳上

6. Stickiness strength: Cut label into 25mm width, one end paste on the plate, with 180° direction pulling the other end of the tape, the pull is stickiness strength. With stickiness strength instrument for testing.

粘力: 将label切成25mm宽, 一端粘于钢板上, 以180°方向的力拉胶带另一端, 所得拉力即为粘力。用粘力测试仪进行测试。

7. The normal temperature test: The range of temperature on plate is -20 ~ 100° C. In 80 ~ 100° C to maintain 8 hours, the label should not be warp, delamination, frothy and so on. The range of temperature on plastic and carton is -20 ~ 65° C. In 65° C to maintain 8 hours, the label should not be warp, delamination, frothy and so on.

正常耐温测试: 在钢板上耐温范围为-20~100° C, 在80~100° C保持8小时后不翘角不分层不脱落不起泡等。在塑胶、纸箱上耐温范围为-20~65° C, 在65° C保持8小时后不翘角不分层不脱落不起泡等。

8. Temperature and humidity cycle test: Cycle conditions (stick on texture (PET), stick on texture/carton (art paper): In temperature of -20 ~ 65° C and humidity of 30~90% to maintain 96 hours, the label should not be warp, delamination, frothy and so on.

耐温湿度循环测试: 循环条件 (贴在塑胶咬花面 (PET) 贴在塑胶咬花面/纸箱 (铜版纸)): 温度-20~60° C, 湿度30~90%, 时间 96小时后不翘角不分层不脱落不起泡等。

9. packing style: exfoliate

包装方式: 片状

10. 其它测试要求详见 (FQ-背胶类产品测试检验规格)

1) 根据 TPV 推行 RoHS 的有关规定, 所有的原材料及辅助材料必须符合 RoHS 的有关规定  
2) 所有原材料的规定物质: 如镉 (Cd) 汞 (Hg) 铅 (Pb) 六价铬 PBB's PBDE's 及镉 (Cd)+汞 (Hg)+铅 (Pb)+六价铬 (针对随机出货的包装材料) 的具体含量依据最新版 RD EMS-01<<供应商环境管理物质管控标准>>的具体限值要求执行

1) According to the rule about RoHS of TPV, All raw material and assistant material and assistant material should accord with the rule of RoHS  
2) All the stated substance of raw material: the actual content of Cd/Hg/Pb/Cr/PBB's/PBDE's and Cd+Hg+Pb+Cr (aim at the packing material with the product), should accord with the latest version of RD EMS-01<<The controlled standard about environment substance for supplier>>.