138h Thistlethwaite St Science and Economic Development (ISED) Canada's Licence-South Melbourne, VIC 3205 exempt RSS standards. Operation is subject to the following two conditions: (1) This device may not cause harmful interference. Australia www.cooltrax.com and (2) this device must accept any interference received. including interference that may cause undesired operation. WG-V3-LTF-AP WG-V3-LTE-NA ACMA: N31242 FCC ID: WSB-UMD3-LTE1 Contains FCC ID: XPYTOBYL280 IC: 10944A-UMD3LTE1 Contains IC: 8595A-TOBYL280 Contains FCC ID: XPY1EHO24NN

Contains IC: 8595A-1EHQ24NN

This device complies with part 15 of the ECC rules and Innovation.

Cooltrax Asia Pacific Ltd.

○ WG-V3-LTE-AP

S/N: UH8888

[BARCODE]





Issued November 2016

MM200STC762 MM200STC1000760

Product Construction Sheet

FLX001622 - FLEXmark® MM 200 SILVER PTP L-23 90 PFW

GENERAL DESCRIPTION:

This is an ink receptive metallized silver polyester film coated with a permanent pressure sensitive acrylic adhesive and backed with a two-side poly coated lay flat release liner.

UL RECOGNITION:

This product is UL recognized. For further information, please reference FLEXcon's UL file number PGGU2.MH10170 or contact your FLEXcon representative.

PRODUCT DATA VALUE TEST METHOD

PHYSICAL PROPERTIES

Thickness Film: 2.0 (51)+/- 10 % ASTM D 3652 (Modified for Adhesive: 1.0-1.1 (25-28) +/- 0.1 (3) mil (micron) use with non-tape product)

+/- 10 % Liner: 6.9 (175)

Dimensional Stability (%) No shrinkage observed On Al panel at 160°F

(71°C) for 24 hr.

ADHESION PROPERTIES*

Adhesion from	Average oz/in (N/m)	
Stainless Steel Acrylic Glass Polypropylene	55 (605) 65 (715) 63 (693) 6 (66)	ASTM D 903 (Modified for 72 hr dwell time)
Expected Shear (hours)	50	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (gm)	1050	ASTM D 2979

For guidance only, not to be used for setting specifications. Due to the custom nature of this product, the data presented are based on three or less production runs.

EXPECTED EXTERIOR LIFE	Two years	
SERVICE TEMPERATURE RANGE	-40°F to 302°F (-40°C to 150°C)	
MINIMUM APPLICATION TEMPERATURE	50°F (10°C)	
STORAGE STABILITY	Two years stored at 70°F (21°C) and 50% RH	
FLEXmark is a registered trademark of	FLEXcon Company, Inc.	12/11/2015

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

FLEXcon, 1 FLEXcon INDUSTRIAL PARK, SPENCER, MA 01562-2642 PHONE 508 885-8200 FAX 508 885-8400

• P: 1300 851 033 • F: 1300 658 889 • graphics@hvg.net.au • www.hvggraphics.com.au